



**DATA / SPECIFICATION SHEET**

# MP 4430

Colour - One side green

**DESCRIPTION**

Our MP 4430 is manufactured by the hot calendering process using high quality non-asbestos fibers and oil resistant synthetic rubber.

**SERVICE**

MP 4430 is a general purpose material suitable for use in wide range of applications, including hot and cold water, steam, oils, fuels, gases and a wide range of general chemicals.

**APPROVALS / COMPLIANCE**

ASTM F 104 P1141A

**AVAILABILITY**

Thickness range = 0.5mm to 5.0mm  
 Standard sheet sizes = 1.5m X 1.0m  
 1.5m X 1.5m  
 1.5m X 2.0m  
 1.5m X 3.0m

**PROPERTIES**

Density		1.7 g/cc
Tensile Strength		13 MPa
Compression		10%
Recovery		40% Min
Ignition Loss		38% Max
ASTM Oil#3	Thickness Increase	15% Max
	Tensile Loss	45% Max
ASTM Fuel B	Thickness Increase	15% Max
	Weight Increase	38% Max

**USE**

Temperature	350°C max
Pressure	30 Bar max
pH Range	4-11

As the company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company