



Colour - Black

Viton (FKM)

DESCRIPTION

Fluorocarbons are now a complex range of polymers. They were first developed in the 1950s to provide a high temperature oil resistant elastomer. They are now an important class of elastomers and capable of providing a very wide chemical compatibility at the temperature up to 200°C.

SERVICE

Resistant to: Mineral oils and greases, some phosphate esters (HFD), silicone oils and grease, chlorinated solvents, air and ozone, fuels.

Not suitable for: Steam and hot water above 100°C, phosphate esters (Skydrol), polar solvents, fuels containing methanol, gear lubricants with EP additives, engine oils with amine additives, amines, alkalis, organic acids, brake fluids.

PROPERTIES

Density	1.9 g/cc
Tensile Strength	6 MPa
Elongation	100%
Hardness	75 ± 5
Temperature Range	-15 °C to 200 °C

AVAILABILITY

Thickness range	= 1.0mm to 6.0mm (standard) or by order
Standard sheet sizes	= 1.2m X 1.0m 1.2m X 2.0m 1.2m X 5.0m 1.2m X 10.0m

As the company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company

MASTERPAC-ASIA COMPANY LIMITED

135/18 Amornphan 205 Tower 2 Bldg., 8th Flr., Soi Nathong Ratchadaphisek Rd., Bangkok 10400 THAILAND
Tel +66-0-2689-5393 to 6 Fax +66-0-2689-5397 to 8 www.mpac-asia.com E-Mail : enquiry@mpac-asia.com