



# HARDCOAT

## CORROSION INHIBITOR



### FEATURES

- Multi-year protection of metal parts for inside storage
- 1500+ hours salt spray resistance on aircraft aluminum
- Durable, dry, transparent film
- Commonly used above floor level of aircraft fuselages
- Resists dripping and running during spray application
- Low odor
- Ready-to-use and can be applied with conventional airless or air-operated spray equipment

### PACKAGES

Net Fill	Part No.
10 oz. (284 grams) aerosol	03316
1 gal. (3.78 liters)	03328
5 gal. (18.93 liters)	03305
55 gal. (208 liters)	03355

### APPLICATIONS

- Aircraft fuselages
- Bare metal
- Cargo sections
- Metal parts and machinery storage
- Offshore drilling equipment
- Outdoor electrical connections
- Outdoor equipment and tools
- Overseas storage or shipments
- Underground installations

Qualified to:

- Boeing BMS-3-23G Type II
- Bombardier CMS 565-06 Type I
- Lockheed Martin Heavy Duty CPC 3a



### PROPERTIES

Appearance/Physical State:  
Viscous Brown liquid

Flash Point: (TCC)  
110°F (43°C) Bulk

HMIS:  
1, 3, 0 (Aerosol)  
1, 2, 0 (Bulk)

Propellant:  
Hydrocarbon /Acetone blend

Salt Spray Cabinet Test (ASTM D117):  
1500+ hours on aluminum

Specific Gravity (water=1):  
0.88

Typical Dried Film Thickness:  
33 microns/1.3 mils

Viscosity at -4°F (25°C):  
34 cSt

VOC:  
50.3% (aerosol), 51.4% (bulk)

% non-volatiles:  
51.9% (bulk)

MATERIAL SAFETY DATA SHEETS AVAILABLE UPON REQUEST OR VISIT OUR WEB SITE :[WWW.LPSLABS.COM](http://WWW.LPSLABS.COM)

**LPS Laboratories** • An Illinois Tool Works Company

P.O. Box 105052 • 4647 Hugh Howell Road • Tucker, GA 30085-5052 • TEL: (800) 241-8334 or (770) 243-8800 • FAX: (800) 543-1563 or (770) 243-8899

Internet Web Site: [www.lpslabs.com](http://www.lpslabs.com)

©2009 LPS Laboratories • LPS® is a registered trademark of Illinois Tool Works • Printed in U.S.A. • All Rights Reserved • Form #2072 • Rev. 1/2009