



DATA / SPECIFICATION SHEET

MP 4430

Colour - One side green

DESCRIPTION

Our MP 4430 is manufactured by the hot calendering process using high quality non-asbestos fibers and oil resistant synthetic rubber.

SERVICE

MP 4430 is a general purpose material suitable for use in wide range of applications, including hot and cold water, steam, oils, fuels, gases and a wide range of general chemicals.

APPROVALS / COMPLIANCE

ASTM F 104 P1141A

AVAILABILITY

Thickness range = 0.5mm to 5.0mm
 Standard sheet sizes = 1.5m X 1.0m
 = 1.5m X 1.5m
 = 1.5m X 2.0m
 = 1.5m X 3.0m
 Standrad roll sizes = Up to a maximum size of
 6.0m X 2.0m

PROPERTIES

Density		1.7 g/cc
Tensile Strength		13 MPa
Compression		10%
Recovery		40% Min
Ignition Loss		38% Max
ASTM Oil#3	Thickness Increase	15% Max
	Tensile Loss	45% Max
ASTM Fuel B	Thickness Increase	15% Max
	Weight Increase	38% Max

USE

Max. Temperature	350°C
Max. Pressure	80 Bar
pH Range	4-11

As the company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company

MASTERPAC-ASIA COMPANY LIMITED

135/18 Amornphan 205 Tower 2 Bldg., 8th Fl., Soi Nathong Ratchadaphisek Rd., Bangkok 10400 THAILAND

Tel +66-0-2689-5393 to 6 Fax +66-0-2689-5397 to 8 www.mpac-asia.com E-Mail : enquiry@mpac-asia.com